

PRODUCT DATA 7100 Floor Coating / 7100NS Anti-Slip Coating

DESCRIPTION

7100/7100 NS is an easy to apply solvent based Alkyd floor coating specially designed for applying on old (>2 years), dry concrete for interior and exterior use. The coating has a good resistance against abrasion and neutral detergents (no alkaline cleaning agents) and is resistance during short contact periods against lubricating oils, fuel, petrol etc.

7100 Floor Coating is available in two versions, standard and anti slip NS (with a special synthetic anti slip additive).

RECOMMENDED USES

7100 Floor Coating can be applied on concrete floors older than 2 years, which are completely clean and dry. It is not recommended to apply on smooth/dense concrete or concrete containing a damp repellent additive, which will prevent a good adhesion.

7100 Floor Coating can also be applied on old good adhering coatings.

7100 can be applied onto metal floors which have been correctly prepared and primed with a suitable Rust-Oleum metal primer.

TECHNICAL DATA

Appearance:	Gloss (60°: ± 90%)
Colour:	See colour chart
Density:	1,0 -1,1 kg/l (depending on colour)
Solids Content:	36 - 40 volume % (depending on colour)
Viscosity:	75 - 80 Krebs Stormer units (7100NS: 85 - 90)
Recommended film thickness:	50 µm dry, equal to 130 µm wet

VOC-content:	456 g/l max.
Ready-to-use mixture:	485 g/l max.
Category:	A/i
EU Limit values:	600 g/l (2007) / 500 g/l (2010)

Drying times	20°C/50% r.h.
To touch:	6 hours
To recoat:	24 hours
Full hardness:	1 week

Coverage

Theoretical:	8,0 m ² /l bij 50 µm dry
Practical:	Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

SURFACE PREPARATION

Remove oil, grease and other contaminations with Rust-Oleum 2901 HARD HAT Cleaner/Degreaser for floors or high pressure- (steam) cleaning in combination with appropriate detergents.

Sand old intact coatings to roughen the surface in order to establish a good adhesion. Check the compatibility with old intact coatings.

During application the surface should be dry and clean.

On porous concrete a first coat should be applied with 7100 diluted with ± 10% white spirit.

Remove curing compounds by means of dust free blasting.

DIRECTION FOR USE

To ensure homogeneity, coating materials should be thoroughly stirred prior to use.

Rust-Oleum Netherlands B.V.

Braak 1, 4704 RJ
P.O. Box 138, 4700 AC
Roosendaal, The Netherlands
T +31 (0)165 593 636
F +31 (0)165 593 600
info.nl@ro-m.com
www.ro-m.com

N.V. Martin Mathys S.A.

Kolenbergstraat 23
B - 3545 Zelem
Halen, Belgium
T +32 (0)13 460 200
F +32 (0)13 460 201
info.be@ro-m.com
www.ro-m.com

Rust-Oleum France S.A.S

11, Rue Jules Verne, B.P. 60039
95322 St-Leu-la-Forêt Cedex
France
T +33 (0)130 400 044
F +33 (0)130 409 980
info.fr@ro-m.com
www.ro-m.com

Rust-Oleum UK Ltd.

Unit 6, Spitfire Close
Coventry Business Park
Coventry, CV5 6UR
United Kingdom
T +44 (0)2476 717 329
F +44 (0)2476 718 930
info.uk@ro-m.com
www.ro-m.com

Rust-Oleum Mathys Italia s.r.l.

Largo Donegani 2
20121 Milano, Italia
T +39 335 10 93 482
info.it@ro-m.com
www.ro-m.com

PRODUCT DATA 7100 Floor Coating / 7100NS Anti-Slip Coating

APPLICATION & THINNING

Brush: Sparingly, if required, with 10% white spirit.

Roller: Sparingly, if required, with 10% white spirit.
In case of roller application it can be necessary to apply 2 coats in order to obtain the recommended film thickness.

Cleanup: Immediately after application using thinner or white spirit.

APPLICATION CONDITIONS

Apply in a dry and well-ventilated area.

REMARKS

Apply 7100 Floor Coating never on alkaline substrates.

SAFETY

Consult Safety Data Sheet and Safety Information printed on the can.

SHELLIFE / STORAGE CONDITIONS

5 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

Rust-Oleum Netherlands B.V.

Braak 1, 4704 RJ
P.O. Box 138, 4700 AC
Roosendaal, The Netherlands
T +31 (0)165 593 636
F +31 (0)165 593 600
info.nl@ro-m.com
www.ro-m.com

N.V. Martin Mathys S.A.

Kolenbergstraat 23
B - 3545 Zelem
Halen, Belgium
T +32 (0)13 460 200
F +32 (0)13 460 201
info.be@ro-m.com
www.ro-m.com

Rust-Oleum France S.A.S

11, Rue Jules Verne, B.P. 60039
95322 St-Leu-la-Forêt Cedex
France
T +33 (0)130 400 044
F +33 (0)130 409 980
info.fr@ro-m.com
www.ro-m.com

Rust-Oleum UK Ltd.

Unit 6, Spitfire Close
Coventry Business Park
Coventry, CV5 6UR
United Kingdom
T +44 (0)2476 717 329
F +44 (0)2476 718 930
info.uk@ro-m.com
www.ro-m.com

Rust-Oleum Mathys Italia s.r.l.

Largo Donegani 2
20121 Milano, Italia
T +39 335 10 93 482
info.it@ro-m.com
www.ro-m.com